



Roca

Seattle

Seattle

A mixture of cement and stone creates this versatile series that comes in a variety of formats in both matte & polished finishes. With two cool tones that complement any space, the Seattle series is sure to add a touch of elegance and comfort.




Seattle Blanco UP 12"x24" R & 24"x48" R

Glazed & Polished Porcelain

◇ □ 35"x35" R - 24"x48" R - 24"x24" R - 12"x24" R

Seattle

Glazed & Polished Porcelain



35"x35" R 24"x48" R 24"x24" R 12"x24" R
90x90 cm 60x120 cm 60x60 cm 30x60 cm



Blanco



35"x35" R UP
I67170022



35"x35" R PO
I67170020



24"x48" R UP
I67170034



24"x48" R PO
I67170032



24"x24" R UP
I67170026



24"x24" R PO
I67170030




12"x24" R UP
I67170024




12"x24" R PO
I67170028



Cinza



35"x35" R UP
I67180022



35"x35" R PO
I67180020



24"x48" R UP
I67180034



24"x48" R PO
I67180032




24"x24" R UP
I67180026



24"x24" R PO
I67180030



12"x24" R UP
I67180024



12"x24" R PO
I67180028

Seattle

Glazed & Polished Porcelain

Technical Specifications

CHARACTERISTICS	STANDARD	DECLARED ASTM	
		Polished	Unpolished
Water Absorption	C373	<=0.5%	<=0.5%
Break Strength	C648	Min. 335	Min. 335
Scratch Hardness	MOH's Scale	3	5
Chemical Resistance	C650	Unaffected	Unaffected
Frost Resistance	C1026	Resistant	Resistant
Group	See FAQ's	3	4
Deep Abrasion - Unglazed Tiles	C1243	Pass	Pass
PEI- Glazed Tiles***	C1027	3	4
Minimum Bond Strength (PSI)	C482	165	165
Dynamic Coefficient of Friction (DCOF)	A137.1	<=0.40	>=0.42
Shade and Texture Rating	CTDA "V"	V3	V3
Facial Dimensions	C499	Pass	Pass
Range of Thickness	C499	Pass	Pass
Warpage	C485	Pass	Pass
Wedging	C502	Pass	Pass

Packaging Info

Size	SF per carton	PC per carton
12"x24"	18.94	10
24"x24"	19.05	5
24"x48"	15.28	2
35"x35"	17.22	2