


Hangar

Hangar

Glazed Porcelain




Cement



48"x48" R F3602E8021



Cement



48"x48" R ABS F3601E8021

Technical Specifications

CHARACTERISTICS	STANDARD	DECLARED ASTM	
		Matte	ABS
Water Absorption	C373	<=0.5%	<=0.5%
Break Strength	C648	330	330
Scratch Hardness	MOH's Scale	4	7
Chemical Resistance	C650	Unaffected	Unaffected
Frost Resistance	C1026	Resistant	Resistant
Group	See FAQ's	3	4
PEI- Glazed Tiles***	C1027	3	4
Minimum Bond Strength (PSI)	C482	165	165
Dynamic Coefficient of Friction (DCOF)	A137.1	<0.40	>0.40
Shade and Texture Rating	CTDA "V"	V3	V3
Facial Dimensions	C499	Pass	Pass
Range of Thickness	C499	Pass	Pass
Warpage	C485	Pass	Pass
Wedging	C502	Pass	Pass

Packaging Info

Size	SF per carton	PC per carton
48"x48" R	30.68	2

2 | Hangar | 3