

June



June

Lines, touch and color merge into June bringing calmness in its purest form. Its stone appearance fuses a careful printing and relief technique with neutral shades of gray or graphite and subtle flashes of light similar to those generated by the sun in natural stone. Once laid out, it faithfully maintains the appearance of a limestone that brings to mind white and pearly sea sands with a soft, diverse texture and rich in nuances.

Glazed Porcelain

2 | June








June

Glazed Porcelain



6|June June|7

Technical Specifications

CHARACTERISTICS	STANDARD	DECLARED ASTM
Water Absorption	C373	<=0.5%
Break Strength	C648	Min. 450
Scratch Hardness	MOH's Scale	5
Chemical Resistance	C650	Unaffected
Frost Resistance	C1026	Resistant
Group	SEE FAQS	4
PEI - Glazed Tiles	C1027	3
Minimum Bond Strength (PSI)	C482	165
Dynamic Coefficient of Friction (DCOF)	A137.1	>=0.42
Shade and Texture Rating	CTDA "V"	V3
Facial Dimensions	C499	Pass
Range of Thickness	C499	Pass
Warpage	C485	Pass
Wedging	C502	Pass

Packaging Info

Size	SF per carton	PC per carton	BX per pallet
12"x36" R	14.32	5	24
24"x48" R	15.50	2	30