

TRAVERTINO

TECHNICAL DATA

Format:	63”X63” R	Type:	Glazed Porcelain	
Color:	All colors available	Thickness:	7.0 mm	
Graphic:	2	Recycled Content:	28% *Pre-Consumer	
	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
WATER ABSORPTION	C373	ISO.10545/3	≤0.5%	≤0.5%
BREAKING STRENGHT	C648	ISO.10545/4	≥ 350	≥350
SCRATCH HARDNESS	MOH’s Scale	EN-101	-	7
CHEMICAL RESISTANCE	C650	ISO-10545/13	Unaffected	Unaffected
FROST RESISTANCE	C1026	ISO-10545/12	Resistant	Resistant
GROUP	SEE FAQS	SEE FAQS	-	3
PEI - GLAZED TILES	C1027	ISO-10545/7	-	IV
MINIMUM BOND STRENGHT (PSI)	C482	-	≥50 psi	165
DYNAMIC COEFFICIENT OF FRICTION (DCOF)	A137.1	-	≥0.42	≥0.42
SHADE AND TEXTURE RATING	CTDA “V”	-	-	V2
FACIAL DIMENSIONS	C499	ISO-10545/2	1.5% Max	Pass
RANGE OF THICKNESS	C499	ISO-10545/2	0.040 Max	Pass
WARPAGE	C485	ISO-10545/2	0.75%	Pass
WEDGING	C502	ISO-10545/2	1.0% Max	Pass